

# Makrolon® AR


## Abrasion-resistant solid polycarbonate sheet



I Line  
Innovative

### Your benefits:

- extreme impact strength
- good abrasion resistance
- excellent weathering resistance
- high clarity



**Makrolon® AR** sheet is an abrasion and enhanced UV resistant polycarbonate sheet that offers glasslike hardness coupled with the impact strength of standard polycarbonate. Additionally, **Makrolon® AR** offers on both surfaces enhanced resistance against yellowing and hazing for an extended service life in high profile architectural glazing. **Makrolon® AR 7099** is a one sided hardcoated sheet which can be used for lamination and printing on the uncoated side.

**Makrolon® AR** has a 10-years warranty against breakage and 7-years warranty against delamination and weathering.

### Applications:

Typical applications for **Makrolon® AR** sheet include transparent sound barriers, school and hospital shelter glazing. **Makrolon® AR** is also used extensively in correctional and psychiatric facilities. Additionally, the product performs well for view windows and machine guards in harsh chemical environments. Due to its scratch-resistant coating, **Makrolon® AR** cannot be formed like other **Makrolon®** sheets.

	Test Conditions	Typical values <sup>(1)</sup>	Unit	Standard
<b>PHYSICAL</b>				
Density		1200	kg/m <sup>3</sup>	ISO 1183-1
Water absorption saturation	water at 23 °C	0.30	%	ISO 62
Water absorption equilibrium	23 °C, 50% relative humidity	0.12	%	ISO 62
Refractive index	Procedure A	1.587	–	ISO 489
<b>MECHANICAL</b>				
Tensile modulus	1 mm/min	2350	MPa	ISO 527-1,-2
Yield stress	50 mm/min	> 60	MPa	ISO 527-1,-2
Yield strain	50 mm/min	6	%	ISO 527-1,-2
Nominal strain at break	50 mm/min	> 50	%	ISO 527-1,-2
Flexural modulus	2 mm/min	2350	MPa	ISO 178
Flexural strength	2 mm/min	90	MPa	ISO 178
Taber abrasion resistance	Δ haze after 100 cycles (500 g CS 10F) after 500 cycles	1 – 4 4 – 9	%	ASTM D1044 & ANSI Z26.1
<b>THERMAL</b>				
Vicat softening temperature	50 N, 50°C/h	148	°C	ISO 306
Thermal conductivity	23°C	0.20	W/(m.K)	ISO 8302
Coefficient of linear thermal expansion	23 to 55°C	0.65	10 <sup>-4</sup> /K	ISO 11359-1, -2
Temperature of deflection under load	1.80 Mpa	128	°C	ISO 75-1, -2
Temperature of deflection under load	0.45 Mpa	140	°C	ISO 75-1, -2

<sup>(1)</sup> These values are measured on injection molded samples, and are not intended for specification purposes.

# Makrolon® AR

## Abrasion-resistant solid polycarbonate sheet



Ideas, innovative, intelligent, interesting... Exolon Group i-line represents the next generation of quality products. This seal guarantees innovative and intelligent first-class solutions at all times for a multitude of requirements.

### Light Transmission:

Test Method according to DIN EN ISO 13468.

The stated thicknesses are not all available as standard. Please ask us for more information.

The stated values are typical values only.

Light transmission in %	3	4	5	6	8	10	12	15
Makrolon® AR clear 8099/ 7099	88	87	87	86	85	83	82	80
Makrolon® AR bronze 8850	50	50	50	50	50			

### Available sizes:

**Makrolon® AR** is available in thicknesses of 3 – 15 mm and in the following sizes; other sizes, colors and sheet thicknesses on request.

### Colors:

Makrolon® AR clear 8099/ 7099

Makrolon® AR bronze 8850

### Sizes:

3,000 x 2,000 mm

3,000 x 2,000 mm

### Permanent Service Temperature:

The permanent service temperature without load is approx. 120°C.

### Fire Rating (\*):

Country	Standard	Rating	Thickness	Colour
Europe	EN13501-1	C s3 d0	2-6 mm	clear 8099
France	NFP 92-501&505 NFF 16-101&102	M2 F2	2 - 12 mm 2 - 12 mm	clear 8099 clear 8099
USA	UL 94	V2 HB V0	0.75 - 1.4 mm ≥ 1.5 mm ≥ 10 mm	all colours all colours clear 8099

(\* Fire certificates are limited in time and scope, always check if the mentioned certificate is valid for the purchased Polycarbonate sheet type at the date of delivery. Polycarbonate sheets may change their fire behavior due to ageing and weathering. The indicated fire rating was tested on new / unweathered Product in accordance with the indicated fire classification standards.

### Impact Resistance:

Country	Standard	Rating	Thickness	Colour
Europe	EN 356	P5A P8B	≥ 4 mm 10 & 12 mm	clear 8099 clear 8099

**Distributed by:**  
**GAT Technologies**  
 21 Aitken Street  
 Williamstown VIC 3016 Australia  
 Ph: 03 9397 0001  
[www.gat.com.au](http://www.gat.com.au)  
[sales@gat.com](mailto:sales@gat.com)

**exolon**  
 GROUP

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance, information and recommendations to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Exolon Group. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.

Makrolon® is a registered trademark, owned and licensed by Covestro Group