

# PRODUCT DATASHEET

## LEXAN™ 8A35 Film

### DESCRIPTION

LEXAN 8A35 is a one side velvet, one side polished transparent polycarbonate film. It offers high temperature resistance, excellent dimensional stability, as well as good printability without pre- treatment making it very suitable for multi-layer printing for applications such as overlays, floor graphics, high-performance labels and in-mould decoration. It can be screen printed using traditional solvent based or water based inks, as well as UV or infrared drying inks and offers ease of processing for thermoforming, embossing, die-cutting, hydro-forming and bending. The velvet texture offers mar resistance, and can be used over light-emitting devices (LEDs).

### TYPICAL PROPERTY VALUES ♦

Property	ASTM Test Method	Units (USCS)	Value	ISO Test Method	Units (SI)	Value
<b>Mechanical</b>						
Tensile Strength @ Yield	ASTM D882	psi	8500	ISO 527	MPa	62
Ultimate	ASTM D882	psi	9000	ISO 527	MPa	65
Tensile Modulus	ASTM D882	psi	300000	ISO 527	MPa	2100
Tensile Elongation at Break	ASTM D882	%	100-160	ISO 527	%	100
Gardner Impact Strength at 0.03" (0.75 mm)	ASTM D3029	ft-lb	23	ISO 6603-1	J	31
<b>Tear Strength</b>						
Initiation	ASTM D1004	lb/mil	1.4-1.8		kN/m	245
Propagation	ASTM D1922	g/mil	30-55		kN/m	10-20
Puncture Resistance (Dynatup)	ASTM D3763	ft-lb	9		J	12
<b>Fold Endurance (MIT)</b>						
0.010" (0.25 mm)	ASTM D2176-69	double folds	130			
0.020" (0.50 mm)	ASTM D2176-69	double folds	35			
<b>Thermal</b>						
Coefficient of Thermal Conductivity	ASTM D5470	Btu/hr/ft <sup>2</sup> /°F/in	1.35		W/m <sup>2</sup> K	0.2
Coefficient of Thermal Expansion	ASTM E831	(x10 <sup>-5</sup> /°F)	3.2	ISO 11359	(x10 <sup>-5</sup> /°C)	7
Specific Heat @40°F (4°C)	ASTM E1269	Btu/lb/°F	0.3		KJ/Kg-°C	1.25
Glass Transition Temperature	ASTM D3417 / D3418	°F	307	ISO 11357	°C	153
Vicat Softening Temperature, B	ASTM 1525-00 modified	°F	323		°C	150
Heat Deflection Temp. by TMA at 1.8 Mpa		°F	290	ISO 75 Modified	°C	135
Brittleness Temperature	ASTM D746	°F	-211		°C	-135
<b>Physical</b>						
Density	ASTM D792	slug/ft <sup>3</sup>	2.3	ISO 1183	kg/m <sup>3</sup>	1200
Water Absorption, 24 hrs.	ASTM D570	% change	0.35	ISO 62	% change	0.35
Surface Roughness (RMS)	ASME B46-1	μ	55			
Surface Energy(1 <sup>st</sup> surface/ 2 <sup>nd</sup> surface)	ASTM D5946-01	-	34/34			
Surface Tension(1 <sup>st</sup> surface/ 2 <sup>nd</sup> surface)	Dyne Pens	Dyne	40-42/38-40			
<b>Optical</b>						
Refractive Index @77°F (25°C)	ASTM D542A	-	1.6			
Light Transmission	ASTM D1003	%	90			
Yellowness Index	ASTM D1925	%	0.9			
Haze	ASTM D1003	%	42			
Gloss over Flat Black min/max @ 60°	ASTM D523-60	-	See chart	ISO 2813	-	See chart
<b>Electrical</b>						
Dielectric Strength at 23°C in oil, short time, 250 micron				IEC 243-1	kV/mm	67
Relative Permittivity				IEC 250		
50 Hz					-	2.99
1 MHz					-	2.93
Dissipation Factor				IEC 250		
50 Hz					-	0.0009
1 MHz					-	0.010
Volume Resistivity				IEC 93	Ohm.cm	10 <sup>15</sup>
Surface Resistivity				IEC 93	Ohm	
Arc Resistance, Tungsten	ASTM D495	S	120			

# PRODUCT DATASHEET

## LEXAN™ 8A35 Film

- These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, Please contact your local SABIC representative or the SABIC Quality Services Department.  
Reported Values are Based on 0.250 mm (0.010") Thickness unless otherwise noted.  
™ Trademark of SABIC.

### MANUFACTURING SPECIFICATIONS

Nominal Gauge Ranges	Min/Max Limit of Nominal
0.010-0.015" (0.250-0.375 mm)	± 5%
0.020" (0.500 mm)	± 3%

#### Americas Headquarters

SABIC Innovative Plastics  
One Plastics Avenue  
Pittsfield, MA 01201  
USA  
T +1-413-448-7125  
Toll-free: 1-800-323-3783  
F +1 (888) 443-2033  
sfscustomerservice@sabic-ip.com

#### European Headquarters

SABIC Innovative Plastics  
Plasticslaan 1  
4612 PX  
Bergen op Zoom  
The Netherlands  
T +31 164 293684  
F +31 164 293272  
Sfs.info@sabic-ip.com

#### Pacific Headquarters

SABIC Innovative Plastics  
Specialty Film & Sheet  
1266 Nanjing Road (W)  
16th Floor, Plaza 66  
200040 Shanghai  
China  
T +86 21 62881088 ext. 6733  
F +86 21 6288 0818

#### E-mail

sfscustomerservice@sabic-ip.com



\* Trademark of SABIC Innovative Plastics IP BV

THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT <http://www.sabic-ip.com> AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. No statement by Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right. SABIC Innovative Plastics is a trademark of SABIC Holding Europe BV

™ Trademark of SABIC.

[sabic-ip.com/sfs](http://sabic-ip.com/sfs)