



PRODUCT PAGE



Material:	Nomex 411
------------------	------------------

Overview:

NOMEX® Type 411 is the uncalendered precursor of NOMEX® Type 410. It is available in five thicknesses (0.13 to 0.58 mm) (5 to 23 mil), with a density of 0.3 and correspondingly lower electrical and mechanical properties. It is used in applications such as motor phase insulation and transformer coil end filler, where high bulk and conformability are of prime importance. NOMEX® Type 411 offers increased impregnability and saturability when compared to NOMEX® Type 410, making it suitable for use in cast resin applications as turn and layer insulation.

Description:

Parameters:

Characteristics	Units	Value	Test Method
Series		411	
Application use		Motor phase insulation and transformer coil end filler	
Shape		Roll	
Thickness		0.38	
Operation temperatures		- 220	
Dielectric Strength	V/mil	240	ASTM D149
Full Wave Impulse	V/mil	450	ASTM D3426
Dielectric Constant at 60 Hz		1.2	ASTM D150
Dissipation Factor at 60 Hz (x 10 ⁻³)		3	ASTM D150

Warranty:**Technical data**

All information and statements contained in this document are based on the manufacturer's or material supplier's sources known to us at the time of filing. PERLON, spol. s r.o. believes them to be reliable in good faith, but the accuracy and/or completeness of such information is not guaranteed. The data should be considered representative or typical only and should not be used for specification purposes. Manufacturers reserve the right to make changes to the design, construction and technical data of products without prior notice.

Use of the product

Many factors beyond the control of PERLON, spol. s r.o. and known only to the user may affect the use and performance of materials in a particular application. Therefore, we recommend that the customer perform their own tests of the suitability and performance of the material for their application and to a responsible extent for reliable results. As a result, the customer is solely responsible for evaluating the product and determining if it is suitable for the customer's application, including evaluating workplace hazards and reviewing all applicable regulations and standards. Failure to properly evaluate, use, or comply with all applicable safety regulations may result in injury, illness, death, and/or property damage if the material and associated safety is not properly evaluated. PERLON, spol. s r.o. makes no warranties of fitness for a particular purpose.

Limitation of liability

PERLON, spol. s r.o. shall not be liable for any loss or damage arising out of or relating to the product material, whether direct, indirect, special, incidental or consequential (including, but not limited to, loss of products or business), regardless of the applicable legal practice, including but not limited to warranty, contract, negligence or strict liability.

www.convertimg.sk