

Material: PLEXIGLAS® XT White WN670 GT

Overview:

PLEXIGLAS® XT White WN670 GT is an extruded acrylic sheet that offers a balance of aesthetic appeal and practical functionality. With its sleek white finish, this material is ideal for various applications where light diffusion and durability are essential.

Description:

Key Features:

- **Translucent Finish:** The sheet provides approximately 78% light transmission, allowing soft light to pass through while maintaining a degree of privacy?
- **Durability:** This acrylic is designed with high break resistance and surface hardness, making it suitable for high-traffic areas and various industrial applications?
- **Temperature Resistance:** PLEXIGLAS® XT White is temperature-resistant up to about 70°C (158°F), ensuring it performs well in a range of environments?
- **UV Protection:** The material is UV absorbent, which helps prevent discoloration and degradation over time
- **Ease of Processing:** This acrylic sheet is easy to cut, drill, and shape, making it ideal for custom applications?

Applications: Common uses include glazing in industrial environments, furniture making, shopfitting, exhibition booth construction, illuminated advertising, and displays. Its combination of visual quality and functional properties makes it a versatile choice for both commercial and residential projects?

Parameters:

Characteristics	Units	Value	Test Method
Series		Plexiglass	
Thickness	mm	2	
Color		Milky white	
Operation temperature	°C	-40 - 70	
Density	g/cm ³	1.19 g/cm ³	ISO 1183
Light Transmission	%	78	ISO 13468-2
Reflexive index	-	1.491	ISO 489
Tensile strength	MPa	72	ISO 527
Flexual strength	MPa	105	ISO 178
Impact strength	kJ/m ²	15	
UV protection	-	1	

Type		Extruded	
------	--	----------	--

Warranty:**Technical data**

All information and statements contained in this document are based on the manufacturer's or material supplier's sources known to us at the time of filing. PERLON, spol. s r.o. believes them to be reliable in good faith, but the accuracy and/or completeness of such information is not guaranteed. The data should be considered representative or typical only and should not be used for specification purposes. Manufacturers reserve the right to make changes to the design, construction and technical data of products without prior notice.

Use of the product

Many factors beyond the control of PERLON, spol. s r.o. and known only to the user may affect the use and performance of materials in a particular application. Therefore, we recommend that the customer perform their own tests of the suitability and performance of the material for their application and to a responsible extent for reliable results. As a result, the customer is solely responsible for evaluating the product and determining if it is suitable for the customer's application, including evaluating workplace hazards and reviewing all applicable regulations and standards. Failure to properly evaluate, use, or comply with all applicable safety regulations may result in injury, illness, death, and/or property damage if the material and associated safety is not properly evaluated. PERLON, spol. s r.o. makes no warranties of fitness for a particular purpose.

Limitation of liability

PERLON, spol. s r.o. shall not be liable for any loss or damage arising out of or relating to the product material, whether direct, indirect, special, incidental or consequential (including, but not limited to, loss of products or business), regardless of the applicable legal practice, including but not limited to warranty, contract, negligence or strict liability.

www.convertimg.sk